

CR0701-880

Content	700 cc
Top out	255x85 mm
Top in	241x72 mm
Bottom	225x56 mm
Useful Height	50 mm
Height	52 mm
Nett weight	13,37 gr
Lubrication	300-40 mg/m ²
Alloy	3003 H22



	EAN-13
CARTON/BOX	
Quantity	EAN-13
350	5 410 797 203 907

POLYBAG	
Quantity	EAN-13

Tolerances : thickness +/- 10%; weights -10%; dimensions +/- 1mm

Packaging	Quantity ctn	Dimensions Ctn			Tare Ctn (kg)	Net Ctn (kg)	Gross Ctn (kg)	Ctn/Layer	Layer/Pal	Ctn/Pal	Quantity palet	Height Pal (m)	Gross Pal (kg)
		L(mm)	W(mm)	H(mm)									
880	880	400	713	295	1,32	11,77	13,09	3	7	21	18.480	2,22	294,80

Made of materials that complies with :

- * Regulation **2004/1935/EC** on material and articles intended to come into **contact with food** and repealing Directive 89/109/EEC
- * European Standard **EN602** "Aluminium and aluminium alloys - Wrought products - Chemical composition of semi products used for the fabrication of articles for use in **contact with food** (Version 07/2004)"
- * Regulation 2006/2023/EC

Lubrication complies with :

- * US Food and Drug Administration FDA21 CFR Ch1 § 172.830 or 178.3910 or 178.3570

Proper conditions of transport, storage and use

- * Long-term storage at 12-24°C and short-term transport at 10-35°C, in an atmosphere as dry as possible.
- * Avoid moisture (wetness, condensation, ...)
- * Allow 2-3 days in intermediate storage, when moving from cold to warm or damp processing rooms.
- * Open packaging 2-3 hours prior to use.
- * Used aluminium alloy can be used within temperature range : -40°C / +250°C (max 60 min). However, content of filled containers can influence these limits.
- * It is recommended to avoid contact with strongly acidic and/or alkaline products.
- * The suitability of uncoated aluminium foil containers for specific applications should be ascertained by the relevant user/customer/packer.