

## RR0104-1000



Content	100 cc
Top out	104 mm
Top in	- mm
Bottom	80 mm
Useful Height	20 mm
Height	20 mm
Nett weight	1,83 gr

**Tolerances :**

\* Thickness +/- 8% (EN546-3)

\* Weight -8%

\* Dimensions +/- 1mm

EAN-13	
CARTON/BOX	
Quantity	EAN-13
1000	5 410 797 100 305

POLYBAG	
Quantity	EAN-13

Packaging	Quantity ctn	Dimensions Ctn			Tare Ctn (kg)	Net Ctn (kg)	Gross Ctn (kg)	Ctn/Layer	Layer/Pal	Ctn/Pal	Quantity palet	Height Pal (m)	Gross Pal (kg)
		L(mm)	W(mm)	H(mm)									
1000	1.000	285	255	260	0,25	1,83	2,08	12	7	84	84.000	1,97	194,55

**Complies with**

- \* Regulation **2004/1935/EC** on material and articles intended to come into **contact with food** and repealing Directive 89/109/EEC
- \* European Standard **EN602** "Aluminium and aluminium alloys - Wrought products - Chemical composition of semi products used for the fabrication of articles for use in **contact with food** (Version 07/2004)"
- \* Regulation 2006/2023/EC

**Proper conditions of transport, storage and use**

- \* Long-term storage at 12-24°C and short-term transport at 10-35°C, in an atmosphere as dry as possible.
- \* Avoid moisture (wetness, condensation, ...)
- \* Allow 2-3 days in intermediate storage, when moving from cold to warm or damp processing rooms.
- \* Give the aluminium appropriate time to climatise by opening boxes a few hours prior to use.
- \* Used aluminium alloy can be used within temperature range : -40°C / +250°C (max 60 min). However, content of filled containers can influence these limits.
- \* It is recommended to avoid contact with strongly acidic, salty and/or alkaline products.
- \* The temperature and contact time have a significant influence on the suitability of uncoated aluminium foil containers for specific applications. Therefore the relevant user/customer/filler/packer should ascertain the suitability of the product for its application.

*Note : Full detailed information can be found on the certificate of conformity (available upon request)*