

RR0304-4x100

Content	1350 cc
Top out	304 mm
Top in	290 mm
Bottom	264 mm
Useful Height	21 mm
Height	23 mm
Nett weight	16,40 gr
Alloy	8666 H25/8006 H24
Lubrification	300-400 mg/m ²



EAN-13	
CARTON/BOX	
Quantity	EAN-13
4 x 100	5 410 797 102 019

POLYBAG	
Quantity	EAN-13
100	5 410 797 102 026

Tolerances : thickness +/- 8% (EN546-3) ; weights -8%; dimensions +/- 1mm

Packaging	Quantity ctn	Dimensions Ctn			Tare Ctn (kg)	Net Ctn (kg)	Gross Ctn (kg)	Ctn/Layer	Layer/Pal	Ctn/Pal	Quantity palet	Height Pal (m)	Gross Pal (kg)
		L(mm)	W(mm)	H(mm)									
4 x 100	400	790	390	545	1,63	6,56	8,19	3	4	12	4.800	2,33	118,26

Made of materials that complies with :

- * Regulation **2004/1935/EC** on material and articles intended to come into **contact with food** and repealing Directive 89/109/EEC
- * European Standard **EN602** "Aluminium and aluminium alloys - Wrought products - Chemical composition of semi products used for the fabrication of articles for use in **contact with food** (Version 07/2004)"
- * Regulation 2006/2023/EC

Lubrification complies with :

- * US Food and Drug Administration FDA21 CFR Ch1 § 172.830 or 178.3910 or 178.3570

Proper conditions of transport, storage and use

- * Long-term storage at 12-24°C and short-term transport at 10-35°C, in an atmosphere as dry as possible.
- * Avoid moisture (wetness, condensation, ...)
- * Allow 2-3 days in intermediate storage, when moving from cold to warm or damp processing rooms.
- * Open packaging 2-3 hours prior to use.
- * Used aluminium alloy can be used within temperature range : -40°C / +250°C (max 60 min). However, content of filled containers can influence these limits.
- * It is recommended to avoid contact with strongly acidic and/or alkaline products.
- * The suitability of uncoated aluminium foil containers for specific applications should be ascertained by the relevant user/customer/packer.